

NOTE:
THE USE OF THIS TREATMENT IS
SUBJECT TO RMS' APPROVAL

FLUSH CONCRETE KERB

150mm SQUARE STONE SETTS. 60mm THICK
WITH 10mm JOINTS OVER 30mm THICK
MORTAR BEDDING & EXFOLIATED FINISH TO
IMPROVE TRACTION.

STONE KERB

CONCRETE GUTTER

KERB RAMP

FOOTPATH

1500

FOOTPATH

KERB RAMP

CONCRETE GUTTER

STONE KERB

FLUSH CONCRETE KERB

ROAD WIDTH VARIES

PLAN 1:100

SLURRY BOND COAT (LATICRETE 3701 + CEMENT)
REFER TO NOTE 2

30mm THICK MORTAR BED.
REFER TO NOTE 3

10mm WIDE JOINTS
REFER TO NOTE 5

150mm WIDE FLUSH
CONCRETE KERB

ROAD

GRANITE SETT ADHESIVE.
LATICRETE 3701 + LATICRETE 290.
REFER TO NOTE 4

200mm THICK 32MPa REINFORCED
CONCRETE BASE. REFER TO NOTE 1

SL82 T&B

100mm THICK DGB20 (98% MMDD)

SECTION 1:10

COMPACTED SUB-GRADE 95%
STANDARD. CONFIRM CBR4 MIN

NOTES:

1. SURFACE SHALL BE MADE PLUMB & TRUE WITHIN 3mm AND SHALL HAVE A WOODEN FLOAT FINISH.
2. MORTAR BED SHALL BE LAID WHILE THE SLURRY BOND COAT IS STILL WET & TACKY.
3. 30mm THICK MORTAR BEDDING FINISHED TO A WOOD FLOAT QUALITY. THE BEDDING SHALL BE OF MODIFIED MORTAR (3:1 SAND:CEMENT) MIXED WITH LATICRETE 3701 MORTAR ADMIX & LATICRETE 226 THICK BED MORTAR AS PER THE MANUFACTURERS'S SPECIFICATIONS.
4. THE GRANITE SETTS SHALL BE ADHERED TO THE CURED BEDDING USING A MIX OF LATICRETE 290 PREMIUM MORTAR & LATICRETE 3701 MORTAR ADMIX AS PER THE MANUFACTURER'S SPECIFICATIONS.
5. USE MODIFIED MORTAR (3:1 SAND:CEMENT) MIXED WITH LATICRETE 3701 MORTAR ADMIX, LATICRETE 226 THICK BED MORTAR TO MATCH SETTS COLOUR.

NOTE: ALL DIMENSIONS IN MILLIMETRES UNLESS OTHERWISE STATED